

# 安徽艾约塔硅油有限公司

## IOTA CORPORATION LTD.

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

### Sealant IOTA SLT 6E

### **Description:**

**IOTA SLT 6E** is a one component, neutral curing, ready-to-use silicone elastomer. It cures quickly at room temperature in the presence of air moisture to give a flexible and strong seal.

### **Examples of applications:**

**IOTA SLT 6E** is a general purpose silicone sealant which offers good performance on many different applications where weather tightness is required:

Doors and windows caulking,

Indoor decoration caulking,

Other construction joint caulking.

### Advantages:

One component, medium modulus and room temperature cure by releasing oxime Thixotropic (non flowing)

Resistance environmental temperature variation from -50°C ~ +150°C

Good adhesion performance on most materials applications, for example, gives adhesion on most glass, ceramics, steel and wood surfaces, polished aluminum.

### Characteristics:

1, Before curing
Type of sealant
oxime
Specific gravity, g/cm <sup>3</sup> , approx
0.98
Flow resistance, mm,
approx1
Extrusion, g/min, approx
260
2, Curing
Skin formation time, min. approx.
4
Curing rate, mm / 1 day, approx
2
mm / 7day, approx 8
Application temperature, °C+5 to
+40
3, After curing



# 安徽艾约塔硅油有限公司

# IOTA CORPORATION LTD.

安徽省蚌埠市高新区兴中路 985 号 日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 Tel: 86-552-3827158

Fax: 86-552-3822922

Shore A hardness,	
approx	
Joint movement capability, %, approx	
20	
Operating temperature, °C50 t	to
+150	
Mechanical properties on a 2 mm thick film after 3 days curing*	
Modulus at 100% elongation, MPa, approx	
0.35	
Tensile strength, MPa, approx	
1.10	
Elongation at break, % approx	
580	
* - 1 - 1 1 1 0000 1 1 1 1 1 1 1	

<sup>\*</sup> at a temperature of 23°C and relative humidity of 50%

### **Processing:**

### Joint dimensions:

The movement capability of sealants as well as local regulations must be considered. Jointwidth should be twice the depth.

### Joint preparation:

The joint faces to be bonded must be clean, dry and free from dust, oil, grease, old sealant and any traces of contaminant which may affect adhesion. Surfaces should be degreased with solvent soaked cloth and then wiped with a clean cloth. To remove dust, use oil-free compressed air.

### **Priming**

For almost substrates, **IOTA SLT 6E** need not primers. Whether use primer or not when applied on special substrates, prior test is recommended.

### Limits of use:

**IOTA SLT 6E** must not be used on materials which can bleed certain substances over time, or directly on surfaces which may react with the oxime products released during curing, such as copper and its alloys.

**Colors:** Translucent. For other colors, please consult us.

<sup>\*\*</sup> To avoid influence adhesion performance, pls warm the sealant above 5°C before application



安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

# IOTA CORPORATION LTD.

安徽艾约塔硅油有限公司

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

### Packaging:

IOTA SLT 6E is available in 195kg drums and 820 kg big bags.

### Storage and shelf-life:

**IOTA SLT 6E** has a shelf life of 12 months from its date of manufacture, when stored at a temperature below 30°C in its original unopened packaging.

After opening the product must be used quickly.

### IOTA CORPORATION LTD.

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

TeL: 0086-552-7183958 Fax: 0086-552-3822922

Whatsapp: 0086-15556181299 WeChat: Amandalin99

QQ: 309136222

Email: <a href="mailto:sales02@siliconeoil.net">sales02@siliconeoil.net</a>
Website: <a href="mailto:www.rtvsilicone.net">www.rtvsilicone.net</a>

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.personalcaresilicone.com