

安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158 传真: 86-552-3822922

IOTA D4926 Two-component silicone sealant

Product features:

IOTA D4926 is a kind of double component silicone rubber, which is cured at room temperature and can be heated quickly. Its characteristics are as follows:

Before curing, good fluidity, the operation time is moderate, good self-decoration, convenient operation and use;

Excellent resistance to high temperature and low temperature performance, after curing can be used under -50 $^{\circ}$ C $^{\circ}$ +200 $^{\circ}$ C;

Excellent electrical insulation, arc resistance and shock resistance, long term protection of electronic components and welding points;

Good water resistance, ozone resistance, earthquake resistance, aging resistance, can effectively prevent the infiltration of water vapor, to maintain long-term sealing performance;

Excellent thermal conductivity, can guarantee the effective heat dissipation of electronic components and batteries.

Application:

Widely used in the new energy automotive power lithium battery PACK, electronic components, waterproof, heat sealing cushion;

Used in various electrical equipment potting, bonding, positioning, sealing and waterproof.

Typical product performance (not used as a product standard)

No	Item	Technical index	Inspection
			method
Before (curing		
1	Appearance	A component B	/
		component	
		White fluid Dark gray	,
		fluid	
2	Viscosity	A component 1000-12	200GB/T 2794
	(mPa.s,25℃)	B component 1000-12	200
3	Applicable period	≥90	/
	(min,25℃)		
4	Curing time	≤50	/



安徽省蚌埠市高新区兴中路 985 号

安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

电话: 86-552-3827158 传真: 86-552-3822922

日月科技园

	(min,>45℃)		
5	Curing time (h,25°C)	≤4	/
After curin	ng (After 24 hours at room	n temperature)	
6	Appearance	Dark gray black elastic rubber	/
7	Density(g/cm3)	1.35±0.05	GB/T 13477
8	Shore A hardness	42-50	GB/T 531.1
9	Tensile strength (Mpa)≥0.35	GB/T 528
10	Volume resistivity $(\Omega.cm)$	1x1014	GB/T 1692
11	Breakdown voltage strength (Kv/mm)	18	GB/T 1695
12	Dielectric constant /1MHz	2.8	GB/T 1693
13	Thermal conductivity (W/ (m.K)	≥1.0	/
14	Flame retardant grade	V-0	GB/T 2408

IOTA CORPORATION LTD.

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

TeL: 0086-552-7183958 Fax: 0086-552-3822922

Whatsapp: 0086-15556181299 WeChat: Amandalin99

QQ: 309136222

Email: sales02@siliconeoil.net Website: www.rtvsilicone.net