



安徽省蚌埠市高新区兴中路 985 号 日月科技园 电话: 86-552-3827158 传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 Tel: 86-552-3827158 Fax: 86-552-3822922

Sealant IOTA SLT 30G

Description:

IOTA SLT 3OG is a one-component silicone sealant which when exposed to atmospheric humidity, cures rapidly to form a permanently flexible and extremely durable weather tight seal. The cured sealant will accommodate joint movement of maximal amplitude of 20 % throughout a wide temperature range; resistance to severe weathering is excellent.

Examples of applications:

IOTA SLT 3OG is a high modulus sealant and should be selected for use on applications where joint loads are high and where relative movement between substrates is to be minimised. When used on external joints a weathertight seal or high integrity will result. All classical glazing joints; Door and window frames; Cladding and curtain wall construction; Shop windows, display cases, panels and signs; Portable buildings, caravans and containers; Construction joints; Swimming pools;

Marine hardware.

Advantages:

IOTA SLT 3OG bonds strongly to clean uncoated glass, ceramics and glazed or painted surfaces without the need to prime. For most other substrates it is recommended that a primer be used, a range of high performance primers is available which will ensure optimal bonding to most commonly encountered substrates. After cure, **IOTA SLT 3OG** will be resistant to many acids and bases diluted and salt spray and will tolerate short exposure to most industrial solvents and hydrocarbon based products, in the latter case some reversible swelling and softening will occur. The exceptional translucent quality of IOTA SLT 3OG is such that it is ideally suited for use where the sealant is visually prominent, examples being, display cases and shop windows.

Characteristics:

1, Before curing





安徽省蚌埠市高新区兴中路 985 号 日月科技园 电话: 86-552-3827158 传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 Tel: 86-552-3827158 Fax: 86-552-3822922

| Type of sealant |
|---|
| Acetic |
| Specific gravity, g/cm ³ ,approx |
| 1.02 |
| Flow resistance ,mm, |
| approx0 |
| Extrusion ,g/min, approx. |
| 180 |
| 2, Curing |
| Tack-free time*. min. approx |
| 6 |
| Curing rate*, mm / 1 day, approx |
| 4 |
| mm / 3 day, approx 8 |
| mm / 7 day, approx 10 |
| Application temperature, $^\circ\!$ |
| +40 |
| 3, After curing |
| Shore A hardness , |
| approx |
| Elastic recovery , %, approx |
| 98 |
| Operating temperature, $^\circ C$, |
| +120 |
| Mechanical properties on a 2 mm thick film after 3 days curing* |
| Modulus at 100% elongation, MPa, approx |
| 0.6 |
| Tensile strength, MPa, approx |
| 2.0 |
| Elongation at break, % approx |
| 350 |
| Mechanical properties on slabs * |
| |
| Modulus at 100% elongation, MPa, approx |
| 0.5 |
| |





安徽省蚌埠市高新区兴中路 985 号 日月科技园 电话: 86-552-3827158 传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 Tel: 86-552-3827158 Fax: 86-552-3822922

* at a temperature of 23°C and relative humidity of 50%

Processing:

Joint dimensions :

The movement capability of sealants as well as local regulations must be considered. Jointwidth should be twice the depth.

Joint preparation:

The joint faces to be bonded must be clean, dry and free from dust, oil, grease, old sealant and any traces of contaminant which may affect adhesion. Surfaces should be degreased with solvent soaked cloth and then wiped with a clean cloth. To remove dust, use oil-free compressed air.

Priming:

For almost substrates, IOTA SLT 3OG need not primers. Whether use primer or not when applied on special substrates, prior test is recommended.

Sealant application:

For good performance it is essential that the sealant is only bonded to the two facing sides of the joint. To achieve this install a backup material (closed cell polyethylene or open cell polyurethane foam). Apply the sealant in a continuous operation making sure all air pockets or voids are eliminated. Tool the sealant with light pressure to spread the material against the joint surfaces. This operation should be made with a dry spatula before skin formation occurs.

Excess uncured sealant should be wiped and cleaned with a commercial solvent, cured sealant can only be removed by scraping (i.e. with a razor blade), or with a special silicone remover product.

Limits of use:

IOTA SLT 3OG must not be used on sensitive surfaces which could react with the acetic acid which is released during cure, nor should it be used on materials where migration of constituents can take place, e.g. certain rubbers.

IOTA SLT 3OG must not be used for structural glazing applications.

IOTA SLT 3OG should not be painted (poor coverage and adhesion of paints).

IOTA SLT 3OG (once cured) can be used in applications in which there is a risk of occasional short term contact with water-based foodstuffs, but under no circumstances should it be used for permanent contact applications.

IOTA SLT 3OG is not recommended where abrasion or physical abuse will be encountered. For all uses in permanent immersion, please consult us.





安徽省蚌埠市高新区兴中路 985 号 传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 Tel: 86-552-3827158 Fax: 86-552-3822922

Colors: Translucent. For other colors, please consult us.

Packaging:

IOTA SLT 3OG is available in 195kg drums and 820 kg big bags.

Storage and shelf-life:

IOTA SLT 30G has a shelf life of 18 months, guaranteed by IOTA from its date of manufacture (the expiry date is shown on the packaging), when stored at a temperature between -5°C to +50°C in its original unopened packaging. After opening the product must be used quickly.

IOTA CORPORATION LTD.

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000 TeL: 0086-552-7183958 Fax: 0086-552-3822922 Whatsapp: 0086-15556181299 WeChat: Amandalin99 QQ: 309136222 Email: sales02@siliconeoil.net Website: www.rtvsilicone.net